

TECHNICAL DATA SHEET
(ÜRÜN TEKNİK SPESİFİKASYONU)

Product Name	NONWOVEN FABRIC FOR REINFORCED TEXTILE 160 GSM					
	<u>Analysis Method</u> <u>Analiz Metodu</u>	<u>Unit</u> <u>Birim</u>	<u>Target Values</u> <u>Hedef Değerler</u>		<u>min</u>	<u>max</u>
Mass per Unit Area (Birim Alan Ağırlık)	NWSP 130.1	g/m ²		160,0	144,00	-
Thickness (Kalınlık)	NWSP 120.6	mm		0,81	0,69	-
Tensile Strength /Dry (Kopma Mukavemeti /Kuru)	NWSP 110.4	N \ 50 mm	MD	480,0	432,00	
		N \ 50 mm	CD	280,0	252,00	
Breaking Elongation /Dry (Kopma Uzaması /Kuru)	NWSP 110.4	%	MD	25,0	21,25	
		%	CD	30,0	25,50	
Dimensional Stability at Hot Air (Sıcakta Çekme)	10 min at 200° C and at 4 kg	%	MD			0,50
		%	CD			0,70

Issue Date
(Yayın Tarihi)
5.02.2025

Approved by
Quality Department