

TECHNICAL DATA SHEET
(ÜRÜN TEKNİK SPESİFİKASYONU)

Product Name	NONWOVEN FABRIC FOR REINFORCED TEXTILE 250 GSM					
	<u>Analysis Method</u> <u>Analiz Metodu</u>	<u>Unit</u> <u>Birim</u>	<u>Target Values</u> <u>Hedef Değerler</u>		<u>min</u>	<u>max</u>
Mass per Unit Area (Birim Alan Ağırlık)	NWSP 130.1	g/m ²		250,0	225,00	-
Thickness (Kalınlık)	NWSP 120.6	mm		1,40	1,19	-
Tensile Strength /Dry (Kopma Mukavemeti /Kuru)	NWSP 110.4	N \ 50 mm	MD	820,0	738,00	
		N \ 50 mm	CD	620,0	558,00	
Breaking Elongation /Dry (Kopma Uzaması /Kuru)	NWSP 110.4	%	MD	30,0	25,50	
		%	CD	35,0	29,75	
Dimensional Stability at Hot Air (Sıcakta Çekme)	10 min at 200° C and at 4 kg	%	MD			0,50
		%	CD			0,50

Issue Date
(Yayın Tarihi)
22.12.2024

Approved by
Quality Department